



(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
19.01.2005 Bulletin 2005/03

(51) Int Cl.⁷: **D21H 21/42**

(21) Application number: **04016542.5**

(22) Date of filing: **14.07.2004**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PL PT RO SE SI SK TR
 Designated Extension States:
AL HR LT LV MK

(72) Inventors:
 • **Phillips, Roger W.**
Santa Rosa, CA 95405 (US)
 • **Raksha, Vladimir P.**
Santa Rosa, CA 95403 (US)
 • **Hollingsworth, Keith**
Healdsburg, CA (US)

(30) Priority: **14.07.2003 US 487527 P**

(71) Applicant: **Flex Products, Inc.**
a JDS Uniphase Company
Santa Rosa, CA 95407-7370 (US)

(74) Representative:
Banzer, Hans-Jörg, Dipl.-Ing. et al
Kraus & Weisert,
Thomas-Wimmer-Ring 15
80539 München (DE)

(54) **Security thread comprising an optically variable structure**

(57) A security thread for embedding in or on a sheet such as a document, currency or packaging is disclosed, wherein the thread has a thin film interference structure (21, 35) deposited thereon. The structure (21, 35) may be a Fabry-Perot structure in the form of a single filter, or may be plural filters, spaced side-by-side.

The thread appears to have separated interference filters deposited thereon. Preferably the thread is first roll coated with oil using an oil-ablation technique to remove deposited material in situ in the coating process. A magnetic layer (52, 66) may be deposited within, behind or in front of the thin film interference structure (21, 35).




FIG. 6

Description

Background of the Invention

[0001] The use of security threads for protecting banknotes, credit cards and other valuable documents is well known. A security thread is a strip of material placed on the surface of a banknote document or sheet such as banknote; alternatively a security thread may be serpentine or woven into the banknote paper (a window type effect) to confer additional security (authenticity) to the bank note. Typical dimensions of a hot stamp thread are a width of 1-5mm, a thickness of 3-4 μm ; windowed polyester terephthalate (PET) based threads have a thickness of about 0.5 mil or 12.5 microns. By way of example, one of the earliest forms of security threads consisted of reflective foil transferred by hot stamping to the surface the banknote (GB 2119312 A). This reflective foil prevented reproduction of counterfeit banknotes by printing processes such as from printing presses, PC printers and copiers. Holograms (EP-A-0624688), holographic features along with thermo chromic features (GB 2347646), opaque coatings having characters and patterns readable by transmitted light in combination with luminescent substances (US 6474695), repeating patterns of magnetic/magnetic indicia or metal dots (WO2103624), laser etching fine lines and text with a laser (German "Auslegeschrift" no. 22 05 428) and (WO02101147), printing micro-characters on a metallized transparent plastic with clear acid resistant inks followed by acid etching of the unprinted areas to produce shiny micro-characters on a transparent base (US 4,652,015), bonded nucleic acid molecules so that complementary nucleic acid molecules can bind to the molecules already attached to the document (DE 10122836), and optically variable security elements using liquid crystal material (EP0435029) have all been used to make security threads. However, these aforementioned threads either take too much time to make and/or have other associated problems; for example, it is found that laser etching takes too long to be cost effective, etching by use of chemicals requires multiple steps and is not considered to be environmentally friendly; holograms can be readily copied, and in many instances the features of the threads are not readily seen by eye by the average person and machines are required to read them.

[0002] A method to pattern a single layer of metal or carbon in a vacuum chamber was advanced in United States Patent 4,022,928 by Piwczyk. Piwczyk used various methods to apply a perfluoropolyether known as FOMBLIN™ or Krytox™ to a substrate requiring a pattern for a vacuum deposited layer. The perfluoropolyether inhibited the deposition of the depositing material to a web or plastic substrate. Application of this fluid was by spray or vacuum evaporation in combination with a selected removal process as with a laser or an electron beam. A printing method was also described. Printing

techniques including relief printing such as letterpress or flexography, planographic printing such as offset lithography, and gravure, and screen-printing such as silkscreen process printing were disclosed.

[0003] Subsequently, Ronchi in United States Patent 4,749,591 incorporated herein by reference, and in PCT application WO 8700208(A1)) advanced this printing process by applying the inhibiting oil, FOMBLIN, to a vacuum roll coater where patterning thin films on plastic substrates was desired.

[0004] Ronchi in U.S. patent 4,749,591 only discloses applying a single layer of metal, for example, aluminum as is shown in Fig. 1, deposited as a vacuum thin film layer. A demetallized aluminum layer in the case of a security thread embedded into a banknote can easily be forged by simply using a metallized polyester that is subsequently patterned by one of the above methods. In an attempt to copy a security thread having a single layer manufactured by Ronchi's technique, patterning by photolithography in combination with a caustic etchant, or by any of the aforementioned processes or even by using a silver pencil to simulate the security thread could be used. Security threads having multi-layer films where one of more of the layers are patterned has not previously been considered. A major impediment to providing several thin film layers, was residual oil remaining on the images and on non-patterned areas of the web. This residual oil was detrimental to further thin film coating since left over oil would cause "ghosting"; a process whereby the inhibiting oil is transferred to the back side of plastic film when roll coating, which in turn causes inhibiting oil to be transferred further down the web on the front side. Left over inhibiting oil also causes adhesion failures to subsequent thin film layers.

[0005] "Ghosting" and the ability to remove residual inhibiting oil is overcome by this invention. By way of this advance, for the first time, patterned multilayer optical stacks could be conveniently manufactured in a cost effective way on a security thread, by roll coating. In particular, a new optically variable security thread that had a high pattern resolution was made that contained readable text or graphic images where covert features such as magnetic signatures could also be incorporated.

[0006] It is an object of this invention, to provide a security thread having optically variable features such as an optically variable pattern that can be seen against a background that is distinguishable from the pattern, or from which the pattern stands out.

[0007] It is a further object of this invention, to provide a relatively simple, inexpensive method of manufacture of a multilayer patterned security thread for use within or upon a web or sheet, for example on currency, documents or packaging for providing authentication thereof.

Summary of the Invention

[0008] According to the invention, these objects are

achieved by a security thread as defined in claim 1 and a method as defined in claim 18. The dependent claims define preferred and advantageous embodiments of the invention.

[0009] In accordance with this invention there is provided, a security thread for embedding within or upon a sheet or document, comprising:

an elongate substrate having a first side and a second side;

an optically variable structure deposited on one of the first and second side of the elongate substrate, wherein the optically variable structure comprises a thin film interference structure which has the appearance of a plurality of separated interference filters arranged side-by-side and spaced from one another having visible color shifting properties in the form of a visible pattern of visually separated distinguishable indicia against one of a foreground and background of a different color.

[0010] This invention provides a security thread providing security to a sheet, document or packaging, wherein thread has a visibly optically variable structure thereon that is visible from at least one side of the sheet; although the optically variable structure may be a continuous plurality of layers forming a large Fabry-Perot cavity or interference filter, by providing a patterned layer in front of the Fabry-Perot cavity, the interference filter appears to be separate spaced filters. In another embodiment plural separated filters are provided which similarly appear as separated optically variable structures.

[0011] In accordance with this invention there is provided, a sheet having a security thread embedded therein or disposed thereon, the security thread comprising:

a substrate having a first side and a second side; a plurality of separated n-layered Fabry-Perot cavities deposited upon the first side of the substrate, side-by-side, wherein the Fabry-Perot cavities are spaced from one another, wherein each n-layered Fabry-Perot cavity is a thin film interference filter having visible color shifting properties; said plurality of cavities being arranged along the substrate to form a visible pattern as a result of the color shifting properties.

[0012] In accordance with another aspect of this invention there is further provided, a security thread for imbedding within or disposing upon a sheet, wherein the security thread comprises a plastic web upon which is deposited layers of thin film color shifting coatings forming side-by-side, spaced apart interference filters, wherein the interference filters are seen as patterns against a background of a different color.

[0013] In accordance with one embodiment of this invention, a continuous Fabry Perot structure having plu-

ral layers defining one or more cavities can be applied to one side of a web or substrate. On a second side of the web, a pattern of aluminum or some other material visibly distinguishable from the Fabry Perot structure can be applied using an oil ablation process. Visually when one views the thread from the patterned aluminum side, the portions absent aluminum show as optical variable regions, and the portions with aluminum present show as contrasting aluminum regions. Hence in this embodiment, the continuous Fabry-Perot structure reveals to the viewer from the patterned side, plural side-by-side spaced FP cavities since the aluminum masks portions providing the pattern.

[0014] In accordance with yet another aspect of the invention there is provided a method for forming an optically variable device comprising the steps of:

patterning a reflective layer on a web substrate having a first side and a second side using an oil-ablation technique to form a patterned reflective layer; removing oil residue from the first side of the web and depositing thin-film layers on the web substrate to form the optically variable device.

[0015] In accordance with another aspect of the invention there is further provided a method of patterning metal comprising the steps of:

applying a non-wetting oil to selected portions of a first surface of a web substrate to create an oil pattern; depositing metal on the first surface of the web substrate wherein the non-wetting oil ablates depositing metal from the oil pattern; and removing oil residue using a first glow discharge applied to the first

surface of the web and a second glow discharge applied to a second surface of the web.

[0016] In accordance with another aspect of the invention there is provided a machine-readable security device, comprising a web having disposed thereon, a patterned layer of magnetic material sandwiched between two metal layers.

[0017] In accordance with the invention a machine-readable security device is also provided wherein a security thread includes a magnetic material patterned thereon using an oil-ablation process.

[0018] The use of an oil ablation process is a preferred embodiment, allowing the coating and removal of a rolled on pattern within a coating chamber to yield a patterned web having a visible patterned interference structure. Notwithstanding, it is within the scope of this invention to use of other materials having similar properties to oil, wherein its removal is compatible with the coating of subsequent layers in situ. Alternatively, but less preferably, a water soluble polymer coating that can later be removed by washing is possible, however temporary

coatings of this sort are not as useful as the application of oil, which can be removed within the deposition chamber.

[0019] This invention circumvents difficulties encountered in wet chemical etching methods for patterning by providing a novel security thread that is optically variable either in reflection or transmission with text or other patterns by using an all-dry process, in-line, in a vacuum roll coater. The human eye can readily see the optical performance of the thread as a color shift as the thread is tilted back and forth. Either the text or pattern is optically variable against a transparent or shiny reflective background, or alternatively the background is optically variable against the text or patterns that can be easily viewed in transmission. Furthermore, the thread and its pattern can be distinguished from the background of the sheet, which carries it. Alternatively, the thread can be viewed in reflection where the imagery appears to be colored or optically variable using foil or color shifting ink against a reflective background of aluminum or other colored metal such as copper, or an optically variable, or a non-optically variable thin film optical stack. Alternatively an embodiment of the invention provides the inverse or negative image of the above-mentioned structures. The optically variable optical stacks can take the form described in United States Patent numbers 4,705,356; 4,838,648; 5,135,812; 5,214,530; 5,278,590; 5,278,590; 6,157,489; 6,241,858; 6,243,204; 6,241,858; 6,569,529; and 6,699,313 to Phillips, an inventor of this invention. In addition, mica based interference pigments such as TiO_2 or Fe_2O_3 coated micas can be used as the color shifting pigments in the color shifting inks.

[0020] Various embodiments of this invention are described and shown in detailed description and accompanying figures. The thread can either be windowed into the banknote in much the same manner as that found in European patent application EP1258334 A3 in the names of Cunningham, and Brian or can be applied across the surface of the banknote.

[0021] Such threads as described in accordance with this invention cannot be accurately reproduced by way of being photocopied, photographed, or printed since these technologies do not possess optically variable effects. Furthermore, in the case of optically variable foil, the optics of copiers prevents even the face color at normal incidence from being imaged; since just a black image results as the reflective surface of the optically variable thread causes the light to miss the entrance optics of the copier. In addition, the intricate design of the text, having a resolution down to 60 microns, would prevent any counterfeiter from using scissors to simulate this security device.

Brief Description of the Drawings

[0022] Exemplary embodiments of the invention will now be described in conjunction with the drawings in

which:

Fig. 1 is a diagram illustrating a prior art device wherein a layer of patterned aluminum on a PET substrate or web.

Fig. 2 is a cross sectional view showing an embodiment of the invention wherein interference structures are shown created by layer of patterned aluminum on a PET web covered with a spacer layer of MgF_2 capped by a Cr layer, the three layers forming a plurality of optical interference structures, side-by-side having windows, therebetween.

Fig. 3 is a cross sectional view of a layered structure with patterned aluminum on one side of a PET web, an optically variable foil coating on the same side of the PET web, and a different optical coating on the other side of the PET web.

Fig. 3b is a cross sectional view similar to that of Fig. 3, with the addition of an embossing of the plastic layer.

Fig. 4 is a diagram of an embodiment illustrating a patterned magnetic layer on a PET web.

Fig. 5 shows an embodiment of the invention wherein a patterned magnetic layer is sandwiched between two layers of aluminum on a PET web.

Fig. 6 shows an embodiment with a patterned aluminum layer on one side of a PET web and an optically variable foil with a hidden magnetic layer on the same side of the PET web.

Fig. 7 is an illustration showing a patterned aluminum layer deposited on a plastic substrate over-coated with color shifting ink on one side of a PET web.

Fig. 8 shows the effect of positive and negative patterned aluminum layer over-coated with color shifting ink layer on one side of a PET web.

Fig. 9 is a diagram of an embodiment of the invention wherein a patterned aluminum layer is deposited on one side of a PET web and a color shifting ink layer is coated on the opposite side of the PET web.

Fig. 10 is a cross sectional view illustrating a patterned aluminum layer deposited on one side of a PET web over-coated with a protective layer of abrasion resistant lacquer and a color shifting ink on the opposite side of the PET.

Fig. 11 shows a patterned aluminum layer over-

coated with a Fabry-Perot design on one side of a PET web and coated with a second different Fabry-Perot design on the second side of the PET.

Fig. 12 is a cross sectional view of a patterned aluminum layer on one side of the PET web and a continuous optical structure on the second side of the PET.

Fig. 13 shows a patterned colored shifting foil and one side of the PET and a printed layer of ink (black or complimentary color to the color shifting foil) on the second side of the PET.

Fig. 14 is a cross sectional view showing a Fabry-Perot design on a PET web where the dielectric spacer layer is patterned.

Fig. 15 is a cross sectional view showing a Fabry-Perot design on a PET web where the absorber layer is patterned.

Fig. 16 is a diagram, which illustrates a simplified coater according to an embodiment of the invention.

Fig. 17 is a diagram which illustrates a cleaning arrangement within the coating chamber to remove residual "inhibiting oil".

Fig. 18 is a view of a one dimensional magnetic bar code pattern hidden within the aluminum layers, wherein the A1 layers are conveniently shown in this figure to be transparent so that the bar code can be seen.

Fig. 19 shows a two-dimensional magnetic bar code pattern hidden within the aluminum layers.

Figure 20 is a photograph which shows the resolution of a text symbol in a patterned optically variable security thread.

Figure 21 is a photograph of a patterned optically variable thread embedded into a bank note in a windowed type format.

Figure 22 is a photograph showing the text of the patterned optically variable thread in a bank note viewed in transmission.

Figure 23 shows a graphic security label formed from a patterned optically variable foil structure on a pressure sensitive adhesive-releasable label paper stock.

Detailed Description

[0023] Referring now to Fig. 2 a layer of patterned alu-

minum 22 on a PET web 20 is shown. This embodiment is not limited to the use of aluminum as a reflector material and other reflecting materials, for example another reflecting metal could be used instead of aluminum. The PET web forms the base of the security thread upon which the layers shown are deposited; however other materials, such as other plastics could be used in place of PET. The Aluminum patterned layer 22 is covered by a spacer layer 24 of MgF₂ deposited over the patterned aluminum and web which forms windows 28 in regions over the web absent the deposited aluminum; a layer of absorber material 26, such as a thin layer of chromium, is deposited over the spacer layer 24. An optical interference structure is formed from the reflector/dielectric spacer/absorber (R/D/Ab) stack over the remaining portions of the patterned metal, but not over the portions of the web where the Al has been removed; these portions where Al has been removed are referred to as window portions. The optical interference structure(s) 21 can be color filters that gives the patterned metal a particular appearance, or one that gives the patterned metal a color-shifting, "optically variable" appearance. The aluminum is patterned by printing an image or pattern onto the plastic web 20 using the "inhibiting oil" and then depositing a thin film of aluminum. Although the exact mechanism by which the oil prevents the sticking of the vacuum deposit to the substrate may not be entirely understood, the process nevertheless works. Various theories have been proposed to explain this phenomenon. One theory invokes the idea that the heat of condensation of the depositing material turns the oil into a gas and in effect ablates the metal away. Another explanation is that the oil simply prevents nucleation of the depositing material and hence the arriving material is scattered away.

[0024] In the embodiment shown in Fig. 2 the Al-MgF₂-Cr stacks each form a Fabry-Perot ("F-P") absorber-spacer-reflector-type optically variable device ("OVD"), which are not formed over the window portions of the web because there is an absence of a Fabry-Perot structure in these areas. The plastic web can be clear, tinted, translucent, or opaque, and the materials chosen for the patterned metal layer and overlying thin films are merely exemplary. After coating the thin-film layers, a protective layer is optionally applied, such as a thin layer of lacquer, not shown, or a thin (e.g. 0.5 mil) plastic film that is adhered to the OVD using laminating adhesives.

[0025] Fig. 3 shows a layer structure, similar to that of Fig. 2 on a front side of a web 30. Patterned aluminum is deposited after using a roll-coater with inhibiting oil to apply a pattern of oil to prevent permanent deposition onto predetermined regions of the web 30 on a "front" side of a PET web. Layers 34 and 36 of MgF₂ and Cr are deposited over the front side to form optical interference structures over the A1; the A1 serves as a reflector in the Fabry-Perot structure(s). Another optical structure 39, such as a reflective layer, an optically variable (OV) layer, a magnetic layer, either continuous or patterned,

either sandwiched between layers of aluminum or as a single layer or fluorescent layer is formed on the "back" side of the web. In this embodiment, a protective layer is optionally applied to both surfaces of the OVD. The optical structure may be opaque or semi-transmissive. In accordance with this invention, in the embodiment where a magnetic layer is sandwiched in between the reflective layer, as is described in United States Patent application number 2002/0160194A1 and WO 02090002(A2), in the name of the same inventor, a cover signature is present. A number in digital code or as in a bar code may be present, that is unseen by the naked eye, and may be for validating the serial number on the bill or the denomination for example, \$50.00.

[0026] In this embodiment, where a magnetic bar code is hidden within the device, it exhibits the same reflective properties as aluminum but has a magnetic signature that can be read with appropriate magnetic detectors. The magnetic detection may be just the presence of a magnetic material as in a magnetic image such as a hidden bar code or a hidden logo, or may be a signal of digital or analog recorded information.

[0027] In accordance with this invention, the thickness of the magnetic layer is preferably between 0.1 and 1.0 microns in thickness. In the prior art, it is known to use a thick layer for example having a thickness of 12 to 13 microns. Notwithstanding, this invention can provide a very thin layer that is detectable by providing a continuous layer of magnetic metal or metal that is detectable by magnets. Thinner layers are advantageous for use with security threads to be imbedded in or on currency so that a large stack of bills do not pile up at an angle when stacked. Furthermore, providing thinner layers ensures that overall thickness of the thread remains relatively thin, which is desired. Hence, the thickness of the magnetic layer should be less than 5 microns and preferably less.

[0028] In the simplest case, as shown in Fig. 4 a single layer 42 of magnetic material may be deposited onto the plastic web 40, patterned by the oil imaging method, and then formed into a security thread, label or hot stamp image. In more complicated structures, the patterned magnetic layer 52 supported by a substrate 50 is sandwiched between two layers of aluminum 54 and 56 as is shown in Fig. 5 or is sandwiched between two layers of aluminum in a Fabry-Perot optical stack shown in detail in Fig. 6 wherein a substrate 60 has deposited thereon a patterned aluminum layer 62; upon the layer 62 is a Cr layer 63 a dielectric layer 64, and a magnetic layer 66 between two Al layers 65 and 67 upon the dielectric layer 64. In the instance where only one side of a security thread is visible, the magnetic layer 66 can be covered by a single layer of aluminum 67 and need not be sandwiched between two such layers.

[0029] Referring now to Fig. 5, a cross-sectional view is shown wherein a plastic substrate 50 has deposited thereon a non-magnetic layer 54 of aluminum. Of course other non-magnetic materials could be used. A pattern

of inhibiting oil is then applied to create a predetermined bar-code pattern of oil dependent upon the design upon the rollers that pick up the oil and coat the plastic web 50. The magnetic layer 52 is subsequently deposited and magnetic material only remains where no oil has been applied during the vacuum coating and cleaning process. A final layer of non-magnetic material 56 effectively sandwiches the magnetic layer 52 between the two non-magnetic layers.

[0030] In an alternative embodiment now shown, one could use an additional layer over a patterned layer to serve as a leveling layer. This could be done by evaporating an organic smoothing layer in vacuum and curing by cross linking as taught by Yializis in United States Patent 6,706,412. In the embodiment described in accordance with this invention, the depth of the vacuum deposition layer is considerably thinner than the thickness of the oil pattern; hence in relation to the oil thickness of about 10,000 Angstroms the small bumps of 1000 Angstroms or less for the vacuum deposited layer would be negligible. Patterning for multilayers could take place on unpatterned regions or even on previously patterned regions.

[0031] Fig 6 is a more complex structure than that of Fig. 5, however the method of manufacture is essentially the same, patterning and depositing subsequent layers.

[0032] In yet another embodiment of the invention the combination of patterned thin film with color shifting ink including but not limited to inks containing pearlescent type pigments based on coated mica, SecureShift® colors (registered to Flex Products), optically variable ink (OVI®, registered to SICPA), inks based on diffractive based pigments or liquid crystal color shifting inks can be present. The pigment may be formed of flat thin film optical structures or may be formed of diffractive flakes as described in US patent 6692830 and PCT patent application WO 03011980A1.

[0033] Referring now to Figs. 7 and 8 an embodiment of the invention is shown that utilizes color-shifting ink. In this instance, the color shifting ink 75 is visible through the holes or windows 76 in the patterned thin film 73. In the simplest case, a patterned aluminum 73 is formed on a plastic film 70 such as polyester terephthalate (PET) and the color shifting ink 75 is coated over the patterned aluminum so that from the opposite side, one sees a color shift with viewing angle through the text or graphic images or appears as background around reflective text or graphics.

[0034] In Fig. 8 is an illustration showing that the background can be non-color shifting and foreground color shifting or vice versa.

[0035] Alternatively the color shifting ink is coated onto the surface opposite the patterned aluminum so that one views the security device from the patterned aluminum side. In this instance, the color shifting ink shows through the openings of the patterned aluminum. As in embodiments described heretofore, the patterned aluminum can have an additional protective layer placed

upon it, such as a scratch resistant lacquer or is laminated to a thin PET sheet typically having a thickness of 0.5 mil or less. Figs 9 and 10 exemplify these structures.

[0036] In Fig. 9 a plastic web 90 has on an upper side thereof, an optically variable structure 92, for example in the form of optically variable ink, color shifting ink, optically variable pigment or a thin film Fabry-Perot cavity structure. On a lower side of the web, a patterned layer of aluminum 94 is shown. In Fig. 10 a color shifting ink layer 106 is disposed upon a plastic substrate 100 and a patterned layer of aluminum 104 is deposited on the lower side of the substrate 100 having a protective lacquer coating 106 over it.

[0037] In one embodiment, the reflective layer is a layer of opaque aluminum, so that the window portions of the patterned layer appear reflective. The backside reflector does not typically form an OV structure with the front side MgF₂-Cr layers because the intervening PET web is relatively thick for use as a spacer in a Fabry-Perot structure in the visible range of light. The window portions appear mirrored, while the front-side F-P structures provide an OVD as is shown in Fig. 3.

[0038] Alternatively, the optical structure on the backside of the web is an optical interference structure; such as a thin-film absorber layer on the PET web, a spacer layer over the absorber layer, and a reflective layer over the absorber layer, thus creating a second F-P structure in addition to the F-P structures on the frontside of the web as is shown in Fig. 11. A reflective backside layer 112a is particularly desirable for security threads with OVDs because the mirror-like background provides a good visual reference to the color change of the front-side OVD. This reflective backside layer also serves as a layer in the optically variable structure defined by the two adjacent layers; a Cr layer 115a, a dielectric layer 111a. Fig. 11 also shows a plastic substrate 110 having a patterned aluminum layer 112, followed by a dielectric layer 111 having a layer of Cr 115 over top.

[0039] Alternatively, a layer of color shifting ink may be applied to the backside of the web. The application of color shifting ink to the backside of the web enables an optically variable (OV) effect when the structure is viewed from either side. When viewed from the backside, the OV effect of the color shifting ink is observed. When viewed from the front side, the OV effect of the color-shifting ink structures formed with the patterned Al layer is observed, in addition to the OV effect of the color shifting ink.

[0040] Turning now to Fig. 12, a PET web 120 is shown with patterned aluminum 112 on the front side and an optical structure on the backside. In one embodiment the optical structure is an organic layer 128 containing Anti-Stokes material in the form of powder. The Anti-Stokes layer fluoresces at a shorter wavelength when illuminated at a longer wavelength. Many suitable materials exist, and are typically applied to the backside of web as very fine particles in a carrier. Powdered Anti-

Stokes material is available from STAR DUST TECHNOLOGIES. The particles are generally light-colored, such as a cream or a light tan color, and fluoresce in a color, such as blue, green, yellow, or orange when irradiated with near IR light, which is outside the visible range. Thus, when the window portions are irradiated with the near IR light, the window portions fluoresce in a visible color. This can be used as a covert security feature because the Anti-Stokes coating is not easily seen by casual observation.

Alternatively, shown in Fig. 13, a patterned optically variable foil comprising a patterned layer of aluminum 132, a dielectric layer 131, and a Cr layer 135 may be formed on one side of the PET and a printed layer of regular ink 136 is printed on the second side of the PET substrate 130. The printed ink 136 is either black in color or is a complimentary color to the normal (90 degree) color of the color shifting foil. In this case, the black or complimentary color shows through the windows of the patterned OVD or in the reversed image, the black or complimentary color layer acts as a background for the color shifting patterned text. For instance, a green to blue color shifting foil would have a magenta printed ink on the second side of the PET; for example, green and magenta are complimentary colors. In both instances, the contrast between the printed ink layer and the color shifting foil allows easy viewing in reflected light. A matching color could also be printed so that the reflected colors of the text only show up at other angles than the one at normal.

[0041] In an embodiment shown in Fig. 3b, the plastic web a plastic film 30 has an embossed surface coated with an aluminum layer 32 on the side opposite the patterned coating 34 so that the holographic imagery or diffractive imagery shows through the holes 36.

[0042] Fig. 14 shows an OVD (optically variable device) formed on a web 140 wherein a reflective layer 142, such as an Al layer is deposited, and an overlying spacer layer, such as an MgF₂ layer 144, is patterned, with the oil-"inhibiting" technique. An absorber layer 146, such as a thin layer of Cr, is deposited over the underlying layers to form OVDs where the reflective, spacer, and absorber layers form an F-P structure. As with the OVD shown in Fig. 3 wherein the optical structure on the backside is a reflective layer, the embodiment shown in Figure 14 may have highly reflective regions proximate to the OVD structures that provide visual references when observing the OVD. In another embodiment, more dielectric layer material can be deposited onto the patterned dielectric so that a color-shifting pattern is formed on top of a different color-shifting pattern, once the final absorber layer has been deposited.

[0043] Fig. 15 shows an OVD formed on a web 150 with reflective and spacer layers 152 and 154 respectively formed on the web and an overlying patterned absorber layer 156. The absorber layer is patterned using the oil-ablation techniques. An OVD is formed where the absorber material remains.

[0044] Fig. 16 shows a simplified coating machine according to an embodiment of the invention. The coater includes an unwind roller 160a, a wind roller 160b, a printing head 162, an evaporation boat 164 and glow discharge elements 166a and 166b. In operation, the printing head 162 receives the "inhibiting oil" oil from the pick-up roller 168 and applies the oil to a PET web 170.

[0045] The oil has the property that it does not readily evaporate in the vacuum of the roll coater, but readily evaporates when subjected to the heat of condensation of the evaporating material. In addition, the oil has the property that it does not spread on the surface of the plastic web i.e. there is little, if any, dot gain.

[0046] The oil must stick to the substrate but not spread beyond the image area that is printed. Ideally, it should have an interaction with the plastic web but not spread. If it spreads beyond the image of the imprinting cylinder, the image will not be faithfully reproduced.

[0047] If the graphic images are in pixel form, it is important that pixels are distinguishable from one another and do not have edges or portions that run into each other. Such an unwanted increase in pixel size is known as dot gain. For very thin layers of oil it likely does not make any difference whether it is wetting oil or non-wetting oil. However, it is preferable that oil not bead up. If the oil was thick and non-wetting, it would simply bead up and run off of the web and not maintain the printed image. The spreading of one material on another is determined by the respective surface energies, γ_A , γ_B and γ_{AB} , where γ_A is the surface tension (i.e. surface energy) of the plastic web, γ_B is the surface tension of the oil and γ_{AB} is the interfacial surface tension. Spreading is determined by the equation $S_{LS} = \gamma_A - \gamma_B - \gamma_{AB}$, where S_{LS} is the spreading coefficient. If S_{LS} is positive, spreading will occur. In other words, γ_A is larger than the sum of γ_B and γ_{AB} which means (γ_B plus γ_{AB}) has a lower surface energy than γ_A . Thus, to minimize energy, spreading will occur. Therefore, S_{LS} should be negative so that spreading of the oil on the plastic substrate does not occur. As mentioned above, spreading would be detrimental since the dot gain would reduce the resolution from the original print image on the patterned imaging roller. The oil also has a low vapor pressure so that it does not evaporate after printing the image onto the web. FOMBLIN or Krytox oils meet the spreading criteria; however, other low vapor pressure oils may be used depending on the substrate being used.

[0048] In operation, the web is advanced to the evaporation boat, which deposits Al or other material on the surface of the web. Process conditions are controlled so that the heat of condensation of the A1 vaporizes the oil where it underlies the Al, removing the Al from the regions that previously had oil. An alternate explanation is that the oil prevents nucleation of the depositing aluminum, i.e. the aluminum does not stick and re-evaporates into the chamber. However, even though the process occurs under vacuum, it was discovered that either

products of oil breakdown and/or residual oil (generally "oil residue") may be present on some portions of the web, including the backside of the web after vacuum deposition. Such residue can degrade the optical performance of OVDs subsequently formed on the web and prevents acceptable adhesion of subsequent thin film layers. It is very difficult to even detect the presence of such residue, absent forming an OVD and evaluating its optical performance. Ghosting, smearing, and other undesirable effects were observed when thin-film OVD structures were deposited on webs with patterned A1 without some cleaning of this residual oil. The A1 was deposited and patterned in one vacuum coater, and the OVDs were deposited in another vacuum coater. It was found that oil residue removal can be performed in the A1 coater after patterning, in the OVD coater before deposition, or that a single vacuum roll coater can be used to deposit and pattern the A1 and to deposit the OVD layers, with an intervening cleaning.

[0049] A glow discharge cleaning technique was used to successfully remove oil residue. Several types of glow discharge cleaning techniques were evaluated, as well as other cleaning techniques. A glow discharge cleaning technique using argon gas was tried, but did not adequately clean the residue of the oil used in the patterning process. IR heaters were used before coating, but oil transfer still occurred, presumably because oil transfer between layers of the web occurred. For example, oil residue on the frontside of the web will be transferred to the backside of the web on the wind roll. In an in-line process that coats the OVD before layers of the web are wound together, frontside cleaning of residue may be sufficient. However, with the oil used in this example, it is believed that some amount of cross-contamination occurred during the patterning process, and cleaning both the frontside and the backside was performed, as shown in Figure 17.

[0050] Many additional features of the coater are omitted, such as tensioning rollers and chamber dividers. Similarly, the web may be held against a drum during the Al deposition/patterning.

[0051] Fig. 17 shows a simplified depositing apparatus for cleaning a patterned web. The patterned web 170 comes off the unwind roller 170b and along a series of tension rollers. The backside of the web is cleaned at a first station with a first glow bar 171, shown as being unshrouded. The frontside of the web is cleaned at a second station 172 further along the web with a glowbar that is shrouded. The shroud is optionally omitted if the glow discharge does not affect other system components. Similarly, cleaning the backside of the web might not be necessary in all embodiments. Oxygen was provided to the glowbar shroud, but could be provided at other locations of the chamber. The oxygen provided at the shroud diffused to the region of the first glowbar to create the cleaning discharge. A chamber divider 179 keeps material from the OV source(s) from depositing on the tension rollers and other system components.

The web is tensioned against a coating drum 178 during deposition of the OV layers. A glow discharge using O₂ as the precursor was found to work well to clean the web of oil residue. Other precursors may be preferred for other oils or liquids, or even for this type of oil residue. In a particular embodiment, a web of PET about 8.5 inches wide was transported through a glow discharge cleaning stage at a speed of 0.5 meters/second. The total current to the backside glowbar and the frontside glowbar was 100 mA and the glowbars were operated at 2,200 Volts. Pure O₂ was provided to the shroud of the frontside glowbar to create a chamber pressure of 5×10^{-3} Torr to remove the residual oil from both sides of the patterned web. An OVD that was formed on the patterned web after cleaning in this fashion showed good optical characteristics, suitable for use in commercial applications.

Further Description of Embodiments of the Invention

[0052] The invention is generally directed toward methods and apparatus for manufacturing imaged foils, as well as security articles including optically variable foils and security labels. In a particular embodiment, an optically variable foil is produced using an all vacuum in-line process.

[0053] A substrate consisting of 0.25 to 5 mil PET, preferably 0.5-1.0 mil (1 mil = 25.4 microns) is first patterned on the web, width 2"-60" or more, with a positive or negative image with perfluorinated polyether as described in US publication "Proceedings of the Fourteenth International Conference on Vacuum Web Coating, October 25-27, 2000 by Aerre Machine. A printing station similar to that described in US 4,749,591 was used and is incorporated herein as a reference. However, the printing method is not necessarily limited to that described in US 4,749,591. For example, other printing techniques may be used include ink-jet printing, flexographic printing, gravure printing or lithographic printing, or even dot matrix printing. In the case of ink-jet printing, it is possible to change the pattern or imagery without breaking vacuum. Advantageously, this allows customized patterns to be created on the plastic roll without the need for a roll on a printing station that requires a pre-imaged print roller. Such patterning with an ink jet process would allow sequential numbering of security labels and other security devices, which is highly advantageous. Multi-layer patterning using a single patterning roll or using different patterns in subsequent thin film layers using the ink jet printing process may be used to create complex graphics or even micro-electronics in the security thread. In particular, a security thread with an optically variable feature may be combined with a hidden magnetic bar code in either one dimension, as in a standard bar code, or in a two dimensions, as in a 2D bar code format. The magnetic layer is hidden between other layers of the thin film design, as for example behind a reflective layer or sandwiched between two

highly reflective aluminum layers as shown in Figs. 18 and 19.

[0054] To insure good image fidelity, the printing station should be situated on the cooled drum immediately before the deposition of the first layer, typically aluminum, but may be any material with a heat of condensation sufficient to vaporize the imaged oil. Other substrates such as polyimide, polyhexadiene, polypropylene, polyethylene, polystyrene, polycarbonate triacetate, biacetate, and polynaphthanate (PEN) may be used instead of the polyethylene terephthalate (PET). With other substrates and other surfaces, patterning oils based on the fundamental surface energies encountered and required low vapor pressures as described above would be used.

[0055] Depositing the first layer that is to be imaged is the next process step to be performed. In the case of an OVD security image that is optically variable, either the reflector layer or the absorber layer may be imaged. In general, any layer may be imaged as long as the oil patterning process produces a discreet oil image. For example, the imaging may occur in the dielectric layer by placing the oil image on the prior-deposited layer. In other words, the reflector layer or the absorber layer may be the layer upon which the oil image is placed. Deposition of a metal layer onto the patterned oil results in explosive evolution of liquid oil into gas, causing the depositing layer to be ablated away. There may be some residual oil (several monolayers of oil) remaining in the patterned area which must be removed in order to this imaged oil from transferring further down the web which would in turn cause ghosting (another image pattern) of any subsequent deposition layers.

[0056] In a typical case, the aluminum layer or the chromium layer is imaged and then the rest of the design is added to complete a Fabry-Perot structure, i.e. A1 (opaque, patterned)/MgF₂ 1 QW @ 400nm to 8QW @ 700nm/Cr 30%T. The low index MgF₂ layer may be substituted by any dielectric material that is highly transmissive in the visible. High index dielectric materials will result in an optically variable foil that is less shifting in color than one that has a large optical shift where a low index dielectric material is used. A partially aluminum layer that has a thickness below the opaque point, for example, thickness in the range 200-800 nm, will give a color shifting film that is partially transparent so that information may be read through the optical stack from the paper, or that is printed on the PET. All color shifts move from long to shorter wavelengths, i.e. from red-to-blue.

[0057] To remove residual oil in the patterned area, an oxygen glow situated right after the deposition source on the cooled drum is used. Glows may also be used on the backside of the web before and after the deposition area. In this instance, the O₂ glow will remove any oil from the backside of the web that might have transferred during the "inking process" or flash over during the deposition process that could end up on the back side during wind-up. Typically, the oxygen glow is run at 2,200 volts

at 100 ma for a 12" wide glow system. Residual oil may be detected on the final coated web by noting the variation in color, for example blotches or ghost like images of the original images.

[0058] Resolution of the image using the flexographic printing process has shown to be as low as 20 microns although 70 microns is nominal. This is shown in Fig. 20. Besides text, a graphic image can be made by processing a scanned image using a FloydSteinburg technique as found in the software program COREL DRAW™. This program converts the image into square pixels, which have good black (image) and white (no image) contrast. After coating, the web is slit into ribbons between 1 and 5 mm wide wherein the text is generally situated in the center of the ribbon. Fig. 21 show the optically variable thread of this invention windowed into a bank note and Fig. 22 shows the text symbols when viewed in transmission.

[0059] Instead of a ribbon, the device may function as a security stick-on label by applying adhesive 232 to one side of the PET and laminating to a release layer 234 supported by paper carrier 236 and die cutting the label 230 as is shown in Fig. 23. The adhesive can be a solvent based or a water-based adhesive. A suitable adhesive is an acrylic adhesive, among many others. Instead of a label, the product could be made into a hot-stamp security product by inserting a release layer between the carrier web and the vacuum deposited layer.

[0060] Of course numerous other embodiments may be envisaged without departing from the spirit and scope of the invention.

Claims

1. A security thread for embedding within or upon a sheet or document, comprising:

an elongate substrate (20; 30; 50; 60; 70; 100; 110; 120; 130; 140; 150) having a first side and a second side;

an optically variable structure deposited on one of the first and second sides of the elongate substrate, wherein the optically variable structure comprises a thin film interference structure (21; 35), which appears as a plurality of separated interference filters arranged side-by-side and spaced from one another having visible color shifting properties in the form of a visible pattern of visually separated distinguishable indicia against one of a foreground and background of a different color.

2. The security thread as defined in claim 1, wherein the visible pattern is made by the steps of:

a) coating the substrate (20; 30; 50; 60; 70; 100; 110; 120; 130; 140; 150) with a first material in

the form of the pattern or its inverse;

b) applying a layer of a second material (22) over the first material and portions of the substrate absent said first material adjacent to where the first material is coated;

c) removing the first material and the layer of the second material covering it, leaving the second material (22) in regions where the substrate was not coated by the first material and, d) coating a third (24) and a fourth (26) layer over the second material (22) to form a plurality of Fabry-Perot filters in discrete regions.

3. The security thread as defined in claim 1 or 2, wherein the first side of the elongate substrate (20; 30; 50; 60; 70; 100; 110; 120; 130; 140; 150) has deposited thereon a first layer of reflective material comprising a plurality of side-by-side, spaced apart reflective regions (22), at least some of the spaced-apart reflective regions forming a first layer of the interference structure (21; 35) comprising a plurality of n-layered Fabry-Perot cavities.

4. The security thread as defined in any one of claims 1 to 3 wherein a second optical structure (128; 136) is deposited on the second side of the elongate substrate (120; 130) and wherein a pattern comprising at least a patterned layer (112; 132) is present on the first side of the elongate substrate (120; 130).

5. The security thread as defined in claim 4 wherein the second optical structure comprises an organic layer (128) containing an anti-Stokes pigment.

6. The security thread as defined in claim 4 or 5 wherein the second optical structure comprises a color shifting ink (136).

7. The security thread as defined in any one of the preceding claims, further comprising a magnetic layer (52; 66) within or behind the interference filters.

8. The security thread as defined in any one of the preceding claims, further comprising a Fabry-Perot structure (112a, 111a, 115a) deposited on an opposite side of the elongate substrate (110) to the separated interference filters (112, 111, 115) and wherein one of the Fabry-Perot structure and the interference filters have windows that allow the other to be seen therethrough.

9. The security thread as defined in any one of the preceding claims further comprising a magnetic layer (52; 66) deposited between at least some of the side-by-side spaced apart interference filters.

10. The security thread as defined in any one of the preceding claims, further comprising a magnetic layer

(52) disposed upon a reflective layer (54) or covered on at least one side by a reflective layer common to the plurality of separated interference filters.

11. The security thread as defined in any one of the preceding claims further comprising a magnetic layer disposed within and/or between or behind the interference filters, wherein the magnetic layer has a thickness of less than about 5.0 microns. 5
12. The security thread as defined in any one of the preceding claims further comprising a magnetic layer disposed within and or between or behind the interference filters, wherein the magnetic layer contains machine readable information for verifying the authenticity of the thread or sheet. 10
13. The security thread as defined in any one of the preceding claims, wherein the security thread is disposed within or upon the sheet, and wherein the sheet forms one of an imaged security label, currency or passport security device. 15
14. The security thread as defined in any one of the preceding claims further comprising color shifting ink (75; 106). 20
15. The security thread as defined in any one of the preceding claims, wherein the thin film interference filter includes a color shifting ink. 25
16. The security thread as defined in any one of the preceding claims, wherein the thin film interference filter includes an optically variable pigment. 30
17. A security thread as defined in any one of the preceding claims wherein the elongate substrate (30) has an embossed diffractive pattern coated with a reflective layer (32) on a side of the substrate (30) opposite to the optically variable structure, such that the embossed pattern is at least partially visible from a side of the substrate (30) having the interference structure (35). 35
18. A method for forming an optically variable device upon a web, comprising the steps of: 40
 - patterning a reflective layer on a web having a first side and a second side using an oil-ablation technique; 45
 - removing oil residue from the first side of the web substrate; and 50
 - depositing thin-film layers supported by the web to form the optically variable device. 55
19. The method as defined in claim 17, wherein the step of patterning the reflective layer is performed on the first side of the web, and wherein the thin-film layers

are deposited on the first side of the web over the patterned reflective layer.

20. The method as defined in claim 17 or 18, further comprising the step of removing oil residue from the second side of the web.
21. The method as defined in any one of claims 17 to 19, further comprising the step of depositing an optical structure over the patterned reflective layer, or behind the reflective layer on an opposite side of the web.
22. The method as defined in any one of claims 17 to 20, wherein the step of removing oil residue comprises using a glow discharge.
23. The method as defined in claim 21, wherein the glow discharge is formed from a precursor comprising oxygen.
24. The method as defined in any one of claims 17 to 22, wherein the oil ablation technique includes the step of applying oil in a pattern with an ink jet device.




FIG. 1
Prior Art




FIG. 2




FIG. 3




FIG. 3b




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19






Fig. 20






FIG. 23



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 04 01 6542

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	WO 01/53113 A (FLEX PRODUCTS INC) 26 July 2001 (2001-07-26) * claims 1-78; figures 8A,8B *	1-4,6,7	D21H21/42
X,D	EP 0 341 002 A (FLEX PRODUCTS INC) 8 November 1989 (1989-11-08) * claims 1-11; figures 1-3 *	1-4,7	
X,D	US 6 157 489 A (WITZMAN MATTHEW R ET AL) 5 December 2000 (2000-12-05) * claims 1-24 *	1-4	
X,D	US 4 705 356 A (BERNING PETER H ET AL) 10 November 1987 (1987-11-10) * claims 1-28; figures 1-5 *	1-4,7	
X,D	US 5 135 812 A (ASH GARY S ET AL) 4 August 1992 (1992-08-04) * claims 1-6; figure 1 *	1,6	
A	US 2003/072931 A1 (HEBRINK TIMOTHY J ET AL) 17 April 2003 (2003-04-17) * the whole document *	1-24	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
A	US 4 242 378 A (ARAI YOSHIAKI) 30 December 1980 (1980-12-30) * the whole document *	1-24	D21H
A	DE 199 28 060 A (WHD ELEKTRON PRUEFTECH GMBH) 21 December 2000 (2000-12-21) * the whole document *	1-24	
A	WO 01/07268 A (ANTON MARIANNE MICHELLE ; DRINKWATER KENNETH JOHN (GB); KAY RALPH (GB)) 1 February 2001 (2001-02-01) * the whole document *	1-24	
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 10 November 2004	Examiner Karlsson, L
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			

EPO FORM 1503 (03.02) (P04031)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 04 01 6542

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

10-11-2004

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0153113	A	26-07-2001	AU 1194901 A	31-07-2001
			CA 2397806 A1	26-07-2001
			CN 1423598 T	11-06-2003
			EP 1252027 A1	30-10-2002
			JP 2003520986 T	08-07-2003
			WO 0153113 A1	26-07-2001
			US 2004101676 A1	27-05-2004
EP 0341002	A	08-11-1989	US 4838648 A	13-06-1989
			AT 123888 T	15-06-1995
			CA 1319052 C	15-06-1993
			DE 68923036 D1	20-07-1995
			DE 68923036 T2	19-10-1995
			EP 0341002 A2	08-11-1989
			ES 2072901 T3	01-08-1995
			GR 3017135 T3	30-11-1995
			GR 3029733 T3	30-06-1999
			HK 1005756 A1	22-01-1999
			JP 2016044 A	19-01-1990
			JP 2960434 B2	06-10-1999
US 6157489	A	05-12-2000	CN 1313953 T	19-09-2001
			EP 1133706 A1	19-09-2001
			JP 2002530712 T	17-09-2002
			WO 0031571 A1	02-06-2000
			US 6243204 B1	05-06-2001
			US 6246523 B1	12-06-2001
			US 6236510 B1	22-05-2001
US 4705356	A	10-11-1987	AT 57770 T	15-11-1990
			CA 1253367 A1	02-05-1989
			DE 3580208 D1	29-11-1990
			EP 0170439 A1	05-02-1986
			JP 2040651 C	28-03-1996
			JP 7069489 B	31-07-1995
			JP 61105509 A	23-05-1986
US 5135812	A	04-08-1992	US 5059245 A	22-10-1991
			US 4434010 A	28-02-1984
			US 5281480 A	25-01-1994
			US 5383995 A	24-01-1995
			US 5648165 A	15-07-1997
			US 5569535 A	29-10-1996
			US 5084351 A	28-01-1992
			US 5653792 A	05-08-1997
			US 5570847 A	05-11-1996

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 04 01 6542

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

10-11-2004

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5135812 A		US 5571624 A	05-11-1996
		US 5766738 A	16-06-1998
		US 5171363 A	15-12-1992
		US 5279557 A	18-01-1994
		AT 76888 T	15-06-1992
		AU 606321 B2	07-02-1991
		AU 6645186 A	25-06-1987
		AU 637900 B2	10-06-1993
		AU 7611391 A	08-08-1991
		CA 1315448 C	30-03-1993
		CA 1329733 C	24-05-1994
		DE 3685566 D1	09-07-1992
		DE 3685566 T2	24-12-1992
		DK 36695 A	03-04-1995
		DK 128393 A	12-11-1993
		DK 628586 A	24-06-1987
		EP 0227423 A2	01-07-1987
		ES 2031454 T3	16-12-1992
		GR 3005337 T3	24-05-1993
		JP 1658351 C	21-04-1992
		JP 3022427 B	26-03-1991
		JP 62260875 A	13-11-1987
		NZ 218573 A	28-11-1989
US 2003072931 A1	17-04-2003	EP 1399767 A2	24-03-2004
		TW 577832 B	01-03-2004
		WO 02095456 A2	28-11-2002
US 4242378 A	30-12-1980	NONE	
DE 19928060 A	21-12-2000	DE 19928060 A1	21-12-2000
		AT 241476 T	15-06-2003
		BG 106133 A	28-06-2002
		BR 0012312 A	14-05-2002
		CA 2374435 A1	21-12-2000
		CN 1355745 T	26-06-2002
		CZ 20014232 A3	13-03-2002
		WO 0076778 A1	21-12-2000
		DE 50002371 D1	03-07-2003
		DK 1185422 T3	15-09-2003
		EP 1185422 A1	13-03-2002
		ES 2199846 T3	01-03-2004
		HU 0201521 A2	28-08-2002
		JP 2003502688 T	21-01-2003
		MX PA01011689 A	30-07-2002
		NO 20016015 A	10-12-2001

EPO FORM P0458

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 04 01 6542

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

10-11-2004

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
DE 19928060	A		PL 351651 A1	19-05-2003
			PT 1185422 T	31-10-2003
			SK 17772001 A3	02-07-2002
			TR 200103242 T2	21-03-2002

WO 0107268	A	01-02-2001	AT 236021 T	15-04-2003
			AU 750857 B2	01-08-2002
			AU 5994500 A	13-02-2001
			BR 0012658 A	09-04-2002
			CA 2380259 A1	01-02-2001
			CN 1123454 B	08-10-2003
			DE 60001955 D1	08-05-2003
			DE 60001955 T2	13-11-2003
			EP 1198358 A1	24-04-2002
			ES 2194755 T3	01-12-2003
			WO 0107268 A1	01-02-2001
			JP 2003505726 T	12-02-2003
			US 6712399 B1	30-03-2004
			ZA 200200472 A	20-01-2003
